

Formaldehyde emission according to Japanese Agricultural Standard for Flooring JAS MAFF 240



Desiccators	(10 ± 1) L, glass
Sample specimen size	10 x (150 x 50) mm
Edge sealing	No edge sealing
Temperature	(20 ± 1) °C
Conditioning	Air-tightly sealed in a vinyl bag at (20±1) °C for more than 1 day
Test duration	24 hours ± 10 min
Limit of quantification	0.05 mg/L